



ASPIRE® COPY PAPER

500
sheet ream

160
whiteness

A4 & A3
sheet size

80
gsm weight

CARBON NEUTRAL





AUSTRALIAN MADE

Aspire® Copy Paper

Aspire® Copy is the perfect paper for all round office use, providing you with superior quality at the right price. Aspire® Copy is a high white, smooth and opaque paper with performance you can count on and is suitable for all types of office machines. Aspire® is proudly made in Australia at the Maryvale Mill which is the largest private employer in Victoria's Latrobe Valley. Your choice helps support thousands of Australian jobs.

Aspire® Copy is certified to the Australian Forestry Standard which confirms that it is made with fibre from sustainably managed plantations and forestry operations. The AFS is globally endorsed by the PEFC, the world's largest sustainable forest management system and is the only standard in forestry management which is accredited by Standards Australia®.

Aspire copy paper is also certified carbon neutral under the National Carbon Offset Standard (NCOS) Carbon Neutral Program.

-  **Smooth & Opaque**
-  **Reliable trouble free printing**
-  **Copy – laser – inkjet compatible**
-  **www.aspireofficeproducts.com.au**

Materials

Major components are Bleached Kraft short and long fibre, filler (calcium carbonate) and starch.

Certification

The pulp and paper mill has the following certifications:

- Quality System AS/NZS ISO 9001:2008
- Environmental System AS/NZS ISO 14001:2004
- OH&S AS/NZS 4801:2001
- PEFC certification for 'AS 4707-2006 Chain of custody for certified wood and forest products', promoting sustainable forest management. For more info: www.pefc.org

Product Technical Info

The table below displays typical values.

Test climate: RC @ 50%RH, 23°C.

Physical Properties	Unit	Typical Values	Method based on
Nominal Grammage	g/m ²	80	AS 1301.405s
Moisture	%	4.5	AS 1301.457s
Thickness (Bulking)	µm	102	AS 1301.426s
Roughness (Bendtsen)	ml/min	145	AS 1301.439s
Porosity (Bendtsen)	ml/min	1550	AS 1301.440s
Cobb 1min (multisheet)	g/m ²	26	AS 1301.411s
Wax Pick	number	16	Tappi 459
Visual Properties			
Opacity	%	91.2	AS 1301.454s
CIE Whiteness	D65/10°	160	ISO 11475
Fluorescence (Δ Brightness)	%	22.2	AS 1301.462s
Dirt Frequency	eba ppm	1.6	Tappi 563

For more information please visit www.aspireofficeproducts.com.au

AUST4211

